

Woodstock Metal Roofing

324 Bell Park Drive Woodstock, GA 30188


770-591-8511

www.woodstockmetalroofing.com


29 GAUGE AND (*) 16" STANDING SEAM COLORS




POLAR WHITE
SR .60 SRI 71



LIGHT STONE
SR .50 SRI 57




SADDLE TAN
SR .48 SRI 55



*ANTIQUE BRONZE
SR .26 SRI 25



EVERGREEN
SR .35 SRI 37



CRIMSON RED
SR .31 SRI 31



*BURNISHED SLATE
SR .28 SRI 27



RUSTIC RED
SR .36 SRI 38



IVY GREEN
SR .28 SRI 27



BERRY
SR .30 SRI 27



*COCOA BROWN
SR .28 SRI 27



*CHARCOAL GRAY
SR .27 SRI 26



ASH GRAY
SR .46 SRI 52



*BLACK
SR .30 SRI 30



GALLERY BLUE
SR .27 SRI 26



OLD TOWN GRAY
SR .42 SRI 47



*GALVALUME

- Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance. ENERGY STAR requires an SR value of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit www.energystar.gov.
- Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit www.usgbc.org.

- Delivery Available
- Contractor Referrals
- Fast Order Turnaround
- Trim and Accessories

Final Color Selection Should Be Made From Actual Color Chips

valspar weather XL paint system

